

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claim 1 (original): A method for producing an organic thin film in which an organic thin film is formed on a surface of a substrate, comprising a step (A) of bringing said substrate into contact with an organic solvent solution comprising a metal-based surfactant having at least one hydrolyzable group, and a catalyst capable of interacting with said metal-based surfactant, wherein a water content within said organic solvent solution is either set or maintained within a predetermined range.

Claim 2 (original): A method for producing an organic thin film according to claim 1, wherein said organic solvent solution is prepared by using from 0.001 to 1 mol, or an oxide-equivalent quantity of 0.001 to 1 mol, of said catalyst capable of interacting with said metal-based surfactant, per 1 mol of said metal-based surfactant.

Claim 3 (original): A method for producing an organic thin film in which an organic thin film is formed on a surface of a substrate, comprising a step (A) of bringing said substrate into contact with an organic solvent solution comprising a metal-based surfactant having at least one hydrolyzable group, and a catalyst capable of interacting with said metal-based surfactant, wherein a water content within said organic solvent solution is maintained within a predetermined range, and said step (A) is repeated at least two times using an identical solution.

Claim 4 (original): A method for producing an organic thin film according to claim 3, wherein in repeating said step (A) two or more times, said step (A) is conducted with two or more substrates using an identical solution.

Claims 5-11 (canceled)

Claim 12 (currently amended): A method for producing an organic thin film according to ~~any one of claim 1 through claim 11~~, wherein a water content within said organic solvent solution is either set or maintained within a range from 50 to 1,000 ppm.

Claim 13 (canceled)

Claim 14 (currently amended): A method for producing an organic thin film according to ~~any one of claim 1 through claim 13~~, wherein said catalyst capable of interacting with said metal-based surfactant is at least one material selected from a group consisting of metal oxides; metal hydroxides; metal alkoxides; chelated or coordinated metal compounds; partial hydrolysis products of metal alkoxides; hydrolysis products obtained by treating a metal alkoxide with a two-fold or greater equivalence of water; organic acids; silanol condensation catalysts; and acid catalysts.

Claims 15-18 (canceled)

Claim 19 (currently amended): A method for producing an organic thin film according to ~~any one of claim 1 through claim 18~~, wherein said metal-based surfactant having at least one hydrolyzable group is a compound represented by a formula (I) shown below:



(wherein, R^1 represents a hydrocarbon group that may contain a substituent, a halogenated hydrocarbon group that may contain a substituent, a hydrocarbon group containing a linkage group, or a halogenated hydrocarbon group containing a linkage group, M represents at least one metal atom selected from a group consisting of a silicon atom, germanium atom, tin atom, titanium atom, and zirconium atom, X represents a hydroxyl group or a hydrolyzable group, n represents an integer from 1 to (m-1), m represents an atomic valence of said metal M, and in those cases where n is 2 or greater, said R^1 groups are either identical or different, and in those cases where (m-n) is 2 or

greater, said X groups are either identical or different, although of (m-n) X groups, at least one X group is a hydrolyzable group).

Claims 20-21 (canceled)

Claim 22 (original): A method for producing an organic thin film in which an organic thin film is formed on a surface of a substrate, comprising a step of bringing said substrate into contact with an organic solvent solution comprising a metal-based surfactant having at least one hydroxyl group, wherein a water content within said organic solvent solution is either set or maintained within a predetermined range.

Claim 23 (original): A method for producing an organic thin film according to claim 22, wherein a water content within said organic solvent solution is either set or maintained within a range from 50 to 1,000 ppm.

Claim 24 (currently amended): A method for producing an organic thin film according to ~~either one of claim 22 and claim 23~~, wherein said metal-based surfactant having at least one hydroxyl group is a compound represented by a formula (III) shown below:



(wherein, R^1 represents a hydrocarbon group that may contain a substituent, a halogenated hydrocarbon group that may contain a substituent, a hydrocarbon group containing a linkage group, or a halogenated hydrocarbon group containing a linkage group, M represents at least one metal atom selected from a group consisting of a silicon atom, germanium atom, tin atom, titanium atom, and zirconium atom, X represents a hydroxyl group or a hydrolyzable group, n represents an integer from 1 to (m-1), m represents an atomic valence of said metal M, and in those cases where n is 2 or greater, said R^1 groups are either identical or different, and in those cases where (m-n-1) is 2 or greater, said X groups are either identical or different).

Claim 25 (currently amended): A method for producing an organic thin film according to ~~any one of claim 1 through claim 24~~, wherein said step of bringing said substrate into contact with said organic solvent solution is conducted within a space that is maintained at a humidity of at least 40% RH.

Claim 26 (currently amended): A method for producing an organic thin film according to ~~any one of claim 1 through claim 24~~, wherein said step of bringing said substrate into contact with said organic solvent solution is conducted within a space that is maintained at a humidity of at least 60% RH.

Claim 27 (currently amended): A method for producing an organic thin film according to ~~any one of claim 1 through claim 26~~, wherein said organic solvent solution is a hydrocarbon-based solvent solution or a fluorinated hydrocarbon-based solvent solution.

Claim 28 (currently amended): A method for producing an organic thin film according to ~~any one of claim 1 through claim 27~~, wherein said organic thin film is a crystalline organic thin film.

Claim 29 (currently amended): A method for producing an organic thin film according to ~~any one of claim 1 through claim 28~~, wherein said organic thin film is a monomolecular film.

Claims 30-34 (canceled)

Claim 35 (original): A self-assembly film forming solution for forming a self-assembly film on a surface of a substrate, wherein molecules for forming said self-assembly film form an aggregate within said solution.

Claim 36 (original): A self-assembly film forming solution according to claim 35, wherein molecules for forming said self-assembly film are molecules of either a metal-based surfactant having at least one hydroxyl group or hydrolyzable group, or a derivative thereof.

Claim 37 (currently amended): A self-assembly film forming solution according to ~~either one of claim 35 and claim 36~~, wherein said aggregate is obtained by treating a metal-based surfactant having at least one hydroxyl group or hydrolyzable group with a catalyst capable of interacting with said metal-based surfactant, and water.

Claims 38-40 (canceled)

Claim 41 (currently amended): A self-assembly film forming solution according to ~~any one of claim 35 to claim 40~~, wherein an average particle diameter of said aggregate is within a range from 10 to 1,000 nm.

Claim 42 (currently amended): A self-assembly film forming solution according to ~~any one of claim 35 to claim 41~~, wherein a zeta potential of said aggregate is equal to or greater than a zeta potential of said substrate within an identical solution.

Claim 43 (canceled)

Claim 44 (original): A chemically adsorbed film formed on a substrate, wherein said substrate is not crystalline, and said chemically adsorbed film is crystalline.

Claims 45-48 (canceled)

Claim 49 (original): A method for producing a monomolecular film, comprising a step of applying an organic solvent solution comprising a metal-based surfactant having a hydroxyl group, hydrocarboxy group, or acyloxy group to a substrate, using at least one method selected from a

greater, said X groups are either identical or different, although of (m-n) X groups, at least one X group is a hydrolyzable group).

Claim 58 (new): A method for producing an organic thin film according to claim 3, wherein said step of bringing said substrate into contact with said organic solvent solution is conducted within a space that is maintained at a humidity of at least 40% RH.

Claim 59 (new): A method for producing an organic thin film according to claim 3, wherein said step of bringing said substrate into contact with said organic solvent solution is conducted within a space that is maintained at a humidity of at least 60% RH.

Claim 60 (new): A method for producing an organic thin film according to claim 3, wherein said organic solvent solution is a hydrocarbon-based solvent solution or a fluorinated hydrocarbon-based solvent solution.

Claim 61 (new): A method for producing an organic thin film according to claim 3, wherein said organic thin film is a crystalline organic thin film.

Claim 62 (new): A method for producing an organic thin film according to claim 3, wherein said organic thin film is a monomolecular film.

Claim 63 (new): A method for producing an organic thin film according to claim 22, wherein said step of bringing said substrate into contact with said organic solvent solution is conducted within a space that is maintained at a humidity of at least 40% RH.

Claim 64 (new): A method for producing an organic thin film according to claim 22, wherein said step of bringing said substrate into contact with said organic solvent solution is conducted within a space that is maintained at a humidity of at least 60% RH.

Claim 65 (new): A method for producing an organic thin film according to claim 22, wherein said organic solvent solution is a hydrocarbon-based solvent solution or a fluorinated hydrocarbon-based solvent solution.

Claim 66 (new): A method for producing an organic thin film according to claim 22, wherein said organic thin film is a crystalline organic thin film.

Claim 67 (new): A method for producing an organic thin film according to claim 22, wherein said organic thin film is a monomolecular film.